

ProRox® WM 960^{ES}

ProRox WM 960^{ES} is a lightly bonded heavy duty stone wool mat stitched on galvanised wired mesh with galvanised wire. Stainless steel mesh, stainless steel binding wire and/or aluminium foil facing are available upon request. The wired mat is especially suitable for industrial applications such as high-pressure steam pipes, reactors, furnaces, etc. where high demands are made on the temperature resistance of the insulation.



Product properties

Properties	Performance								Norms
Thermal conductivity at mean temperature	T_m (°F)	100	200	300	400	500	600	700	ASTM C177
	λ (BTU.in/hr.ft ² .°F)	0,27	0,34	0,42	0,53	0,64	0,75	0,86	
	T_m (°C)	38	93	149	204	260	316	371	
	λ (W/mK)	0,039	0,049	0,060	0,076	0,092	0,108	0,124	
Maximum use temperature	1,200 °F (650 °C)								ASTM C447
Linear Shrinkage	≤ 2% at 1,200 °F (650 °C)								ASTM C356
Reaction to fire	Surface burning characteristics Flame spread index = 0; Smoke development index = 0 Non-Combustible								ASTM E84 IMO 2010 FTPC
Nominal density	6.2 lb/ft ³ / 100 kg/m ³								ASTM C167
Corrosion resistance	Evaluation on external stress corrosion cracking tendency of austenitic stainless steel = Passed								ASTM C692 / ASTM C795
	Chemical analysis for Cl ⁻ , F ⁻ , Na ⁺ , SiO ₄ ⁴⁻ : Results fall within acceptability limits of ASTM C795								ASTM C871 / ASTM C795
	Trace quantity of water leachable chloride ions: ≤ 10 mg/kg								EN 13468
Water vapour sorption	< 1% Weight								ASTM C1104
Water absorption	< 0.2 lb/ft ² (1 kg/m ²)								EN 1609

Compliance

- ProRox WM 950^{ES} wired mats fully comply with the requirements as set by internationally recognized standards like EN 14303, CINI 2.2.02, VDI 2055, ASTM C592-16 Type I, II.
- Above product properties reflect only to ASTM standards. Compliance and Performance according to European (EN) standards can be found on our website. Please contact our sales representatives for an extended list of approvals & certifications.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.