

# SeaRox® SL 620

SeaRox SL 620 is a semi-rigid slab made of stone wool. The product can be supplied with reinforced alu foil or glass cloth.



## Application

SeaRox SL 620 is primarily used as part of approved A constructions for Deck and Bulkhead. A-15, A-30 and A-60 steel constructions approved according to IMO 2010 FTP Code.

## Product properties

Properties	Performance		Norm
Thermal conductivity	T (°C) $\lambda$ (W/mK)	10 0,035	EN 12667
Nominal density	100 kg/m <sup>3</sup>		EN 1602 / IMO
Compressive strength	-		EN 826
Fire classification	Non-combustible Approved for A constructions Low Flame-Spread Properties		IMO 2010 FTP Code
Water absorption (short term)	< 1 kg/m <sup>2</sup>		EN 1609 AC
Max. Application Temperature	Wool: 750°C Facing: 80°C		-
Sound absorption directly mounted	$\alpha_w = 0,80$ Thickness: 40 mm	$\alpha_w = 0,90$ Thickness: 60 mm	ISO 354 (approximated) Evaluated after ISO 11 654
Facings	Reinforced alu foil White glass cloth 210 g/m <sup>2</sup> (GW200)		IMO 2010 FTP Code

## Dimensions

### SeaRox SL 620

Thickness (mm): 25-75 mm Length (mm): 1000 mm Width (mm): 600 mm

Local variations in standard dimensions might occur.



0575

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.